

COMFORT

12 GSM SPUNMELT(SMS) WHITE HYDROPHOBIC

Property	Standard	Unit	Value MD/CD
Tensile strength	WSP 110.4	N/50 mm	28/11
Elongation at peak	WSP 110.4	%	55/60
Elongation at 5 N	WSP 110.4	%	1.8/16.5
Elongation at 10 N	WSP 110.4	%	5.0/39
Hydrostatic head	WSP 80.6	mm	160
Air permeability	WSP 70.1	l/m ² /s	2400

Style number: B10120AB

Produced in: Denmark

Rev. 003

All values are indicative